

Densit® WearSpray 2000

Chemically Bonded Corundum-Ceramic

Densit® WearSpray 2000 wear resistant linings provide excellent protection against moderate wear at temperatures up to 400°C (750°F).

Consumption at 25 mm	
Densit® WearSpray 2000	63 kg/m ²
Densit® WearSpray fibers	63 g/m ²
Densit® Anchoring mesh	1 m ² /m ²
Densit® Curing Compound	0.25 l/m ²
Consumption at 40 mm	
Densit® WearSpray 2000	101 kg/m ²
Densit® WearSpray fibers	101 g/m ²
Densit® Anchoring mesh	1 m ² /m ²
Densit® Curing Compound	0.25 l/m ²

DENSIT® WEARSPRAY 2000

- Install mesh
- Mix dry compound with water and fibers
- Convey material through recommended pump
- Spray mixed material onto mesh
- Smooth the surface if required
- Apply Densit® Curing Compound
- For more details refer to the "Densit® WearSpray Video"

Densit® WearSpray 2000 is a trowellable one-component ready-mix delivered in 25 kg bags.

Product must be kept completely

dry until used.

A paddle mixer must be used for mixing the compound. A significant change in consistency of the material (from a dry powder to wet mortar) must be observed within 3 minutes from addition of water.

Avoid making contact with aluminium or galvanized steel when using Densit® compound. Densit® WearSpray 2000 should be installed on a standard expanded metal mesh welded on the steel casing and can even be installed overhead.

Technical Data



The figures given are typical values.
The dry mortar is quality inspected in accordance with the Densit ISO 9001:2000 certified by Lloyd's Register Quality Assurance.

Please contact Wear-Concepts for further information.

PROPERTIES	Standard	Densit® WearSpray 2000
Density	kg/m ³ (lb/ft ³)	EN 1015-6 2625 (164)
Compressive strength	MPa	EN 12190 110
Flexural strength	MPa	EN 196-1 12
Dynamic E-modul	MPa	EN 60-70 10 ³
Casting shrinkage	vol. %	0.2
Thermal conductivity	w/m°C	1.5
Coeff. of thermal expansion	1/°C (1/°F)	EN 1770 10x10 ⁻⁶ (5.6x10 ⁻⁶)
Heat capacity	KJ/kg°C	0.9-1.0
Max. service temperature	°C (°F)	400 (750)
Abrasion resistance	cm ³ /50cm ²	DIN 52108 1.5-2.0
Erosive resistance	min/cm ²	100
Chemical composition	% CaO % SiO ₂ % Al ₂ O ₃ + TiO ₂ % Fe ₂ O ₃ % Cr ⁶⁺	EN 196-10 13 35 50 <0.2 <0.0002
Bag size	kg	25
Pallet size	kg	1250

Your Complete Resource for
Innovative Wear Solutions

1-816-587-1923
fax: 1-816-587-2055

1-888-4WEARCON
email: densit@wearcon.com